

TABOREC R BOPP 3-7 MIX

Description

TABOREC R BOPP 3-7 MIX is a PP regranulate from a stable source of BOPP foil.
The grade is available in mixed colour and packed in big bags of 1000 kg.

Properties

Properties		Test method	Unit	Typical values
Physical	Melt Flow Index (230°C/2,16 kg)	ISO 1133	g/10 min	3,0 - 7,0
	Ash content	ISO 3451-1	%	0 - 5,0
	Density	ISO 1183-1	g/cm ³	0,94
	Volatiles	ČSN 64 0311	%	0 - 0,2
Mechanical	Tensile Strength	ISO 527	MPa	29
	Flexural Modulus	ISO 178	MPa	1 200
Impact	CHARPY Notched Impact Strength	ISO 179-1/1eA 23°C	kJ/m ²	3,8
	CHARPY Unnotched Impact Strength	ISO 179-1/1eU 23°C	kJ/m ²	NB
Notes* The above values (ranges) are typical for this material, not standardized.				