

VALOX™ RESIN VX4910

REGION EUROPE

DESCRIPTION

10% Glass reinforced nucleated PBT/ASA with excellent mechanical properties high dimensional stability, and low density.

TYPICAL PROPERTY VALUES

Revision 20181114

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	80	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	80	MPa	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	3	%	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	3	%	ASTM D638
Tensile Modulus, 5 mm/min	4600	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	115	MPa	ASTM D790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	115	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	3400	MPa	ASTM D790
Tensile Stress, yield, 5 mm/min	80	MPa	ISO 527
Tensile Stress, break, 5 mm/min	80	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	3	%	ISO 527
Tensile Strain, break, 5 mm/min	3	%	ISO 527
Tensile Modulus, 1 mm/min	4600	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	120	MPa	ISO 178
Flexural Stress, break, 2 mm/min	115	MPa	ISO 178
Flexural Strain, break, 2 mm/min	4	%	ISO 178
Flexural Modulus, 2 mm/min	3800	MPa	ISO 178
Ball Indentation Hardness, H358/30	100	MPa	ISO 2039-1
Hardness, Rockwell R	120	-	ISO 2039-2
IMPACT			
Charpy Impact, unnotched, 23°C	45	kJ/m ²	ISO 179/2C
Charpy Impact, unnotched, -30°C	20	kJ/m ²	ISO 179/2C
Izod Impact, unnotched, 23°C	440	J/m	ASTM D4812
Izod Impact, unnotched, -30°C	340	J/m	ASTM D4812
Izod Impact, notched, 23°C	55	J/m	ASTM D256
Izod Impact, notched, 0°C	50	J/m	ASTM D256
Izod Impact, notched, -30°C	45	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	45	J	ASTM D3763
Izod Impact, unnotched 80*10*4 +23°C	30	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	25	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	5	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 0°C	5	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	5	kJ/m ²	ISO 180/1A
Charpy Impact, notched, 23°C	6	kJ/m ²	ISO 179/2C
Charpy Impact, notched, -30°C	5	kJ/m ²	ISO 179/2C

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
THERMAL			
Vicat Softening Temp, Rate A/50	218	°C	ASTM D1525
Vicat Softening Temp, Rate B/50	150	°C	ASTM D1525
HDT, 0.45 MPa, 3.2 mm, unannealed	205	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	130	°C	ASTM D648
CTE, -40°C to 40°C, flow	4.11E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	8.12E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, flow	5.E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	1.2E-04	1/°C	ISO 11359-2
CTE, 23°C to 150°C, flow	3.57E-05	1/°C	ISO 11359-2
CTE, 23°C to 150°C, xflow	1.96E-04	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate A/50	218	°C	ISO 306
Vicat Softening Temp, Rate B/50	150	°C	ISO 306
Vicat Softening Temp, Rate B/120	155	°C	ISO 306
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	205	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	130	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.3	-	ASTM D792
Filler Content	10	%	ASTM D229
Mold Shrinkage, flow, 3.2 mm	0.6 – 0.8	%	SABIC method
Melt Flow Rate, 200°C/3.8 kgf	20	g/10 min	ASTM D1238
Melt Flow Rate, 265°C/5.0 kgf	40	g/10 min	ASTM D1238
Density	1.3	g/cm³	ISO 1183
Melt Volume Rate, MVR at 250°C/5.0 kg	25	cm³/10 min	ISO 1133
Melt Volume Rate, MVR at 265°C/5.0 kg	35	cm³/10 min	ISO 1133
Melt Viscosity, 260°C, 1500 sec-1	160	Pa-s	ISO 11443
ELECTRICAL			
Relative Permittivity, 1 MHz	3.4	-	ASTM D150
Dissipation Factor, 1 MHz	0.02	-	ASTM D150
Relative Permittivity, 1 MHz	3.4	-	IEC 60250
Dissipation Factor, 1 MHz	0.02	-	IEC 60250
INJECTION MOLDING			
Drying Temperature	110 – 120	°C	
Drying Time	2 – 4	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	250 – 270	°C	
Nozzle Temperature	240 – 260	°C	
Front - Zone 3 Temperature	245 – 265	°C	
Middle - Zone 2 Temperature	240 – 255	°C	
Rear - Zone 1 Temperature	230 – 245	°C	
Hopper Temperature	40 – 60	°C	
Mold Temperature	40 – 100	°C	



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.