

Technical Data Sheet

HiPS

Regranulated HiPS Black Extrusio/Spritzguss

	Measurement method	Measuremet condition	Unit	Values
Melt Flow Rate	ISO 1133	200 C; 5 kg	g /10 min	6
Izod Impact Strength at 23°C	ISO 180	notched	kJ/m ²	7
Tensile strength	ISO 527-1	10 mm/min	MPa	1400
Density	ISO 1183-1	method A	g/cm ³	1,06
Mouldschrinkage	Inhouse method		%	0,5-0,8

This information contained in this document is based on testing carried out by our laboratory. To the best of our knowledge and at the time of publication, this information is true and accurate.

It shall however, in no event be held to constitute or imply warranty, undertaking express or implied commitment from the part of supplier. No liability whatsoever can be accepted by supplier