



## INSPECTION CERTIFICATE 3.1

Lot nr. :	0000025238	date :	27/09/2017
Code :	10120303P		
Product :	HAIPLEN H30 G6 BA NERO LP		
Polymer :	PP		
Specification nr.:	10120303P	rev. :	000

REF.: EN 10204

PROPERTIES		Method	Units	SPECIFICATION		LOT VALUES	Conditions
				MIN	MAX		
F05	Density (+23°C)	ISO 1183	g/cm <sup>3</sup>	1,10	1,13	1,12	
F03	Filler content	ISO 3451	%	28	32	30,1	550°C - 1 h
F01	Melt Flow Rate (MFR)	ISO 1133	g/10 min	3	7	4,9	230°C - 2,16 kg
M05	Tensile Modulus	ISO 527-1,2	MPa	5400		6200	50 mm/min
M07	Elongation at Break	ISO 527-1,2	%	4		4,3	50 mm/min
M01	IZOD Notched Impact	ASTM D256	J/m	65		107	+23°C
T02	Softening Temperature - 5 kg (VST/B/50)	ISO 306	°C	120		133	50°C / h

NOTES:

Laboratory Manager:

Varani Paolo

*This certificate has been produced electronically and is therefore not signed.*

TARO PLAST s.p.a. reserved information. The data listed here has been determined using injection molded specimens according to TARO019 specify.