

LDPE
REGRANULATE

General information

Product name	PE transparent
Produced in	Czech Republic
Visual appearance	Granulate
Colour	Transparent
Application	Film production or other purposes
Extrusion	Yes
Blow molding	Yes
Injection	No
Packaging	Big bags



Specification / Stated parameters

LDPE Transparent	Measurement values	Test method
Density (g/cm ³)	0,918	EN ISO 1183-1
MFR 190/2,16 (g/10min)	0,79	EN ISO 1133
MFR 190/5,00 (g/10min)	3,39	EN ISO 1133
Thermal (°C)	190	EN ISO 11357
Filtration (µm)	115-125	
mesh	24x110	
Moisture (%)	≤ 0,05	

*The data above represents the typical ranges of values for each parameter. This data is indicative only and is intended to help manufacturers to select the suitable application. Any deviation from these values alone cannot be claimed as a reason for a complaint or a request for price reduction.

VH-FB Euro, s.r.o.
www.vh-fb-euro.com
sales1@vh-fb-euro.com
IČ: 29113466
VAT: CZ2913466

VH-FB EURO, s.r.o.
Hlavní 329/78, 352 01 AŠ
IČ: 29113466 DIČ: CZ29113466
Tel.: 00420 726 199 689