

## PROPERTIES

	Test method	Unit	Typical value
MFR (230 °C/2.16 kg)	ISO 1133-1	g/10 min	3.0
Tensile stress at yield *	ISO 527-1,2	MPa	33
Tensile strain at yield *	ISO 527-1,2	%	11
Modulus of elasticity in tension *	ISO 527-1,2	MPa	1600
Flexural modulus *	ISO 178	MPa	1600
Izod impact strength (notched, 23 °C) *	ISO 180/A	kJ/m <sup>2</sup>	6
HDT (0.45 MPa, flatwise) *	ISO 75-1,2	°C	94
Rockwell hardness *	ISO 2039/2	R scale	100

Typical properties, not to be used as specification.

\* Average mechanical property values of several measurements carried out on standard injection-moulded test specimens prepared in accordance with ISO 1873-2.