

Natural Flake IV - 09.07.2025

6h - 160°C / 285°C - 3min - 10g

Sample	IV, dl/g	Note
1	0.724	
2	0.715	
3	0.72	
4	0.72	
5	0.75	
6	0.746	
7	0.72	
8	0.71	
9	0.716	Гума
10	0.73	
11	0.74	
12	0.75	
13	0.76	
14	0.75	
15	0.765	
16	0.74	
17	0.75	
18	0.73	
19	0.765	
20	0.73	
21	0.7	FLEXX LLC - Україна
$\bar{X}$, [dl/g]	0.737	