

Technical Data Sheet

SIPOLPRENE® 72220

DESCRIPTION

SIPOLPRENE® 72220 MD is an ether ester thermoplastic elastomer (TPC-ET), manufactured by Sipol, with a nominal hardness of Shore D 72 and a specific copper deactivation stabilisation package that make it suitable for jacketing of those cables working at high temperatures. According to its rheological behaviour, the product can be processed in injection moulding or in extrusion.

THERMAL PROPERTIES

PROPERTY	TEST METHOD	M.U.	TYPICAL VALUE
Melting temperature	ISO 11357-3	°C	218
Crystallization temperature	ISO 11357-3	°C	183
Glass transition temperature	ISO 11357-2	°C	28
Vicat A /50	ISO 306	°C	210

RHEOLOGICAL PROPERTIES

PROPERTY	TEST METHOD	M.U.	VALUE
MFI 230 °C, 2.16 Kg	ISO 1133	g/10 min	19
MVR 230 °C, 2.16 Kg	ISO 1133	cm ³ /10min	15

MECHANICAL PROPERTIES

PROPERTY	TEST METHOD	M.U.	TYPICAL VALUE
Shore D hardness, instantaneous / 15 s	ISO 868	Shore D	72/69
Stress at break	ISO 527	MPa	53
Elongation at break	ISO 527	%	460
Flexural modulus	ISO 178	MPa	660
Izod impact resistance/notched (23°C)	ISO 180	J/m	46
Izod impact resistance/notched (-40°C)	ISO 180	J/m	36
Abrasion resistance (Vertical load 5N)	ISO 4649	mm ³	76
Compression set (23°C)	ISO 815:1991	%	18
Compression set (70°C)	ISO 815:1991	%	70

OTHER PROPERTIES

PROPERTY	TEST METHOD	M.U.	TYPICAL VALUE
Density	ISO 1183	g/cm ³	1,25
Water absorption (23°C x 24 h immersion)	MI 08	%	0.1

Technical Data Sheet

SIPOLPRENE® 72220

PROCESSING CONDITIONS

Suggested temperature profile for injection molding

MELTING TEMPERATURE	MOLD TEMPERATURE	NOZZLE	FRONT ZONE 3	CENTER ZONE 2	REAR ZONE 1
°C	°C	°C	°C	°C	°C
218	40 - 50	240	230	220	195-210

Suggested temperature profile for extrusion

MELTING TEMPERATURE	MFI	FEEDING ZONE	COMPRESSION ZONE	METERING ZONE	HEAD/DIE
°C	g/10 min.	°C	°C	°C	°C
218	19 (230 °C, 2.16 Kg)	200 - 215	215 - 225	215 - 230	215 - 230

DRYING CONDITIONS

Drying recommended = Yes
Drying temperature = 90 °C
Drying time, dehumidifier dryer = 2-3 h
Processing moisture content = 0,15%

PACKAGING

25 kg bags equipped with an aluminum film barrier against moisture action.
500 kg cardboard octabins equipped with an inner PE liner.
500 Kg and 1000 Kg big bags.

STORAGE

Product is stable for 12 months when stored unopened in its original packaging, kept in a cool and dry place and protected from light. When stocked around 5 – 10°C or below, it is recommended to keep it at 15 – 20°C for at least for 24 hours before using it.