

Adstif HA840R



High Crystallinity Polypropylene

Product Description

Adstif HA840R is a nucleated homopolymer which features very high crystallinity, outstanding rigidity and high gloss.

Adstif HA840R is selected by customers for the production of stiff injection moulded articles where high rigidity is needed.

Typical applications of Adstif HA840R include food packaging containers, housewares, small appliances and technical parts.

Regulatory Status

For regulatory compliance information, see Adstif HA840R [Product Stewardship Bulletin \(PSB\) and Safety Data Sheet \(SDS\)](#).

This grade is not intended for medical and pharmaceutical applications.

This grade is supported for use in drinking water applications.

Status	Commercial: Active
Availability	Africa-Middle East; Europe
Application	Caps & Closures; Furniture; Housewares
Market	Consumer Products; Rigid Packaging
Processing Method	Injection Molding
Attribute	Homopolymer; Medium Flow; Ultra High Stiffness

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	20	g/10 min	ISO 1133-1
Density, (23 °C)	0.90	g/cm ³	ISO 1183-1
Mechanical			
Tensile Modulus	2300	MPa	ISO 527-1, -2
Tensile Stress at Yield	41	MPa	ISO 527-1, -2
Tensile Strain at Break	12	%	ISO 527-1, -2
Tensile Strain at Yield	6	%	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched, (23 °C, Type 1, Edgewise, Notch A)	2	kJ/m ²	ISO 179
Thermal			
Vicat Softening Temperature, (A50)	158	°C	ISO 306
Heat Deflection Temperature B, (0.45 MPa, Unannealed)	110	°C	ISO 75B-1, -2
Optical			
Gloss, (60°)	95	%	ASTM D2457

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.