Technical Data Sheet Chemicals



REPSOL ALCUDIA 1970M

The grade REPSOL ALCUDIA 1970M is a low density polyethylene grade of medium fluidity intended for those injection moulding applications in which good mechanical and good flow properties are required. Its formulation does not contain additives.

Applications

- · Caps and closures.
- Medium to large sized Industrial parts and components.

Recommended melt temperature range from 180 to 230°C. Processing conditions should be optimised for each production line.

PROPERTIES	VALUE	UNIT	TEST METHOD
GENERAL			
Melt Flow Rate (190°C, 2.16kg)	8	g/10 min	ISO 1133
Density	919	kg/m³	ISO 1183
MECHANICAL			
Flexural Modulus	140	MPa	ISO 178
Tensile strength at break	9	MPa	ISO 527-2
THERMAL			
Vicat Softening Temperature (10 N)	89	°C	ISO 306
OTHERS			
Shore hardness D	47	-	ISO 868

Storage

The grade REPSOL ALCUDIA 1970M should be stored in a dry atmosphere, on a paved, drained and not flooded area, at temperatures under 50°C and protected from UV radiation. Storage under inappropriate conditions could initiate degradation processes or undesired migration of additives included in its formulation which may have a negative influence on the processability and properties of the transformed product.

Disclaimer

This grade complies with the European regulations for materials for use in food contact. This grade is not intended to be used in medical, pharmaceutical, or healthcare applications, therefore Repsol does not authorize its use in them.





Technical Data Sheet Chemicals



Repsol does not grant express or implicit guarantees that extend beyond the description contained herein. Nothing herein shall constitute any guarantee of merchantability or fitness for a particular purpose. Before using a product sold by Repsol, users must make their own independent determination that the product is safe, legal, and technically suitable for its intended use. Repsol does not assume any responsibility for the use of its materials together with other materials.

Related documents

The following related documents are available on request, and represent various aspects on the usability and safety of the product:

- · Safety data sheet
- · Statement on compliance with food contact regulations

Recommended consumption period: 12 months from the raw material reception

July 2021