

# CYCOLAC™ RESIN MG94

REGION ASIA

## DESCRIPTION

Superior flow, injection molding ABS. Good impact. For thin-wall applications.

## TYPICAL PROPERTY VALUES

Revision 20170706

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, yld, Type I, 5 mm/min	46	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	35	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	2	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	18	%	ASTM D 638
Tensile Modulus, 5 mm/min	2480	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	79	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2620	MPa	ASTM D 790
<b>IMPACT</b>			
Izod Impact, notched, 23°C	240	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	21	J	ASTM D 3763
<b>THERMAL</b>			
Vicat Softening Temp, Rate B/50	98	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	95	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	82	°C	ASTM D 648
CTE, -40°C to 40°C, flow	8.82E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	8.46E-05	1/°C	ASTM E 831
Relative Temp Index, Elec	60	°C	UL 746B
Relative Temp Index, Mech w/impact	60	°C	UL 746B
Relative Temp Index, Mech w/o impact	60	°C	UL 746B
<b>PHYSICAL</b>			
Specific Gravity	1.04	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm (5)	0.5 – 0.8	%	SABIC method
Melt Flow Rate, 230°C/3.8 kgf	11.7	g/10 min	ASTM D 1238
Melt Viscosity, 240°C, 1000 sec-1	1720	Poise	ASTM D 3825
Melt Flow Rate, 220°C/5.0 kg	12	g/10 min	ISO 1133
<b>FLAME CHARACTERISTICS</b>			
UL Recognized, 94HB Flame Class Rating (3)	1.52	mm	UL 94

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>INJECTION MOLDING</b>			
Drying Temperature	80 – 90	°C	
Drying Time	2 – 4	hrs	
Drying Time (Cumulative)	8	hrs	
Maximum Moisture Content	0.1	%	
Melt Temperature	205 – 245	°C	
Nozzle Temperature	205 – 245	°C	
Front - Zone 3 Temperature	205 – 225	°C	
Middle - Zone 2 Temperature	200 – 210	°C	
Rear - Zone 1 Temperature	190 – 200	°C	
Mold Temperature	50 – 70	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	30 – 60	rpm	
Shot to Cylinder Size	50 – 70	%	
Vent Depth	0.038 – 0.051	mm	

## DISCLAIMER

The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC as referred to herein means any legal entity belonging to the group of companies headed by Saudi Arabia Basic Industries Corporation.