

PP FRUIT BOX regrind

Post-industrial PP regrind from fruit / vegetable crates



Material source — PP fruit crate bales



PP FRUIT BOX regrind

Material and quality

PP box (fruit crate), unwashed

Shape and size

Regrind ~ 10 mm

Melt Flow Index

**12.1 g/10 min
(230°C, 2.16 kg)**

MFR per LVS EN ISO 1133-1:2022 — RTU Polymer Materials Testing Laboratory, Test Report No. 2208

Color

Black

DENSITY

Average density of sample

1.068 g/cm³

Per LVS EN ISO 1183-1:2019 — immersion fluid: ethanol ($\rho=0.806$ g/cm³), 22.8°C — Test Report No. 2208

ASH CONTENT

Average ash content

10.96 %

Per LVS EN ISO 3451-1:2019 — direct calcination method @ 750°C (1h) — Test Report No. 2208

DELIVERY

Packaging

**Big-bags, max
1000 kg**

Delivery on pallets

1 x 1 m

One truck load

22-26 big-bags

DOCUMENT REFERENCE
PP-FRUITBOX-20260921

DATE ISSUED
21.09.2026

PREPARED BY
Roberts Petrovičs