



PP

SINTAC 05 I 1087 White

PP Injection

I. Applications

Injected articles.

II. Characteristics

Parameter	Limits	Unit	Method
Melt Flow Index	4-6	g/10min	ISO 1133 (2,16 Kg / 230°C)
Density	0.90	g/cm ³	ISO 1183
Humidity	<0.08	%	INTERNAL METHOD
Ash Content	<10	%	INTERNAL METHOD

III. Packaging / Storage of granulate

- Palettes of 60 bags (25 kg of granulate each).
- Big bags with +/- 1250 kg each.
- Cistern Truck with +/- 25000 kg.

We advise to store the granulate (palettes or big bags) in a covered area.

In case of buying big bags we advise to store it in area which have a little thermic amplitude in order to avoid condensations phenomenon inside the packs.

IV. Comments

Quality parameters of this recycled product have been obtained from random samples. Therefore, the specifications should be taken as an orientation, which may show certain variations among the range agreed with the customer. The processor will be responsible of the storage, transformation and final use of the product.

Technical specification

Et. 1.7
Issued:05 / 11 /2018