

Vydyne® R530H BK0201

polyamide 66



Vydyne R530H BK0201 is general purpose, 30% glass-filled, heat-stabilized, high viscosity PA66 based resin designed for injection molding applications. R530H BK0201 offers standard flow with a black surface finish and maintains the excellent resistance typical of PA66 in chemicals, machine and motor oils, solvents, and gasoline.

General

Additive	• Heat Stabilizer	• Lubricant	
Features	• Antifreeze Resistant • Gasoline Resistant • Hydrolysis Resistant	• Chemical Resistant • Good Flow • Lubricated	• Fatigue Resistant • Heat Stabilized • Solvent Resistant
Agency Rating	• ASTM, D4066 PA012G30	• ASTM, D6779 PA012G30	• RoHS Compliant
Automotive Specifications	• Modine GM0280-A/B • Valeo NVB 15009 Class 3 • Valeo NVB 15007 Class 2B • Tesla TM-1006 v3 - 201130 • Renault AS26 • Mercedes-Benz DBL 5409 (compliance) • HMG MS211-47 Type 2A • GM GMW16270P-PA66-GF30 • Chery Motor Q-SQR.S1-33-2012 CMP.PA66.G6 • Aisin TO20141124 - P-PA66-GF30-807	• VW PV 3936 (compliance) • Valeo NVB 15008 Class 3 • Toyota TSM5603G, Class 2B, Rev 5 (compliance) • Tesla TM-1006 v3 - 101130 • PSA Peugeot-Cotroën FTM64 0046 • Mahle SD2-181 (AR.06576) Rev. 7 • GM GMW3038P-PA66-GF30J • Ford WSS-M4D752-B1 • CATL MS-00000037 – PA66-GF30-X-I02 • VW TL 52682 (compliance)	• VW PV 1015 (compliance) • Valeo NVB 15007 Class 3A • Tesla TM-1006 v3 - 301130 • Stellantis 01994_14_00088 • Mercedes-Benz DBL5406-PV21 (compliance) • Li Auto QLia53100058 • GM GMW3038P-PA66-GF30H • Denso MSR-21-001 • BMW GS 93016
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Injection Molding		

Physical	dry	cond.	Unit	Test Standard
Density	1.38	-	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow : 23°C, 2.00 mm	0.9	*	%	
Flow : 23°C, 2.00 mm	0.4	*	%	
Water Absorption				ISO 62
23°C, 24 hr	1.3	*	%	
Equilibrium, 23°C, 50% RH	1.9	*	%	

©2024 Ascend Performance Materials Operations. The Ascend Performance Materials name, brands, marks and logos (e.g., those identified with ®, ™, or SM) are owned by Ascend Performance Materials Operations, unless otherwise noted.

Mechanical	dry	cond.	Unit	Test Standard
Tensile Modulus (23°C)	11000	7900	MPa	ISO 527-2
Tensile Stress (Break, 23°C)	200	136	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	3.1	4	%	ISO 527-2
Flexural Modulus (23°C)	9400	6400	MPa	ISO 178
Flexural Strength (23°C)	268	158	MPa	ISO 178
Impact	dry	cond.	Unit	Test Standard
Charpy Notched Impact Strength				ISO 179/1eA
+23°C	11	14	kJ/m ²	
-30°C	10	9.8	kJ/m ²	
-40°C	10	9.7	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
+23°C	76	100	kJ/m ²	
-30°C	66	71	kJ/m ²	
-40°C	66	69	kJ/m ²	
Notched Izod Impact Strength				ISO 180/1A
+23°C	11	14	kJ/m ²	
-30°C	10	9.5	kJ/m ²	
-40°C	10	9.4	kJ/m ²	
Thermal	dry	cond.	Unit	Test Standard
Heat Deflection Temperature				ISO 75-2/A
1.80 MPa, Unannealed	248	243	°C	
0.45 MPa, Unannealed	260	258	°C	
Melting Temperature	262	*	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow : 23 to 55°C, 2.00 mm	19	*	E-6/K	
Transverse : 23 to 55°C, 2.00 mm	81	*	E-6/K	
RTI Elec				UL 746
0.750 mm	140		°C	
1.50 mm	140		°C	
3.00 mm	140		°C	
RTI Imp				UL 746
0.750 mm	120		°C	
1.50mm	120		°C	
3.00 mm	120		°C	
RTI Str				UL 746

Vydyne® R530H BK0201

polyamide 66



0.750 mm	125	°C
1.50 mm	140	°C
3.00 mm	140	°C

Electrical	dry	cond.	Unit	Test Standard
Volume Resistivity (1.00 mm)	1E11	-	Ohm*m	IEC 60093
Dielectric Strength (1.00 mm)	40	28	kV/mm	IEC 60243
Arc Resistance (3.00 mm)	6			ASTM D 495
Comparative Tracking Index (3.00 mm)	250 - 399		V	IEC 60112
High Amp Arc Ignition (HAI)				UL 746
0.750 mm	PLC 0			
1.50 mm	PLC 0			
3.00 mm	PLC 0			
High Voltage Arc Tracking Rate (HVTR), 3.00 mm	PLC 1			UL 746
Hot-wire Ignition (HWI)				UL 746
0.750 mm	PLC 4			
1.50 mm	PLC 3			
3.00 mm	PLC 4			

Flammability	Value	Unit	Test Standard
Burning Rate, 2.00 mm		mm/min	ISO 3795
Flammability			UL 94
0.750 mm	HB		
1.50 mm	HB		
3.00 mm	HB		
Glow Wire Flammability Index			IEC 60695-2-12
0.750 mm	675	°C	
1.50 mm	675	°C	
3.00 mm	675	°C	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.750 mm	700	°C	
1.50 mm	700	°C	
3.00 mm	700	°C	

Injection	Value	Unit
Drying Temperature	80	°C
Drying Time	4	h
Rear Temperature	280 - 310	°C
Middle Temperature	280 - 310	°C

©2024 Ascend Performance Materials Operations. The Ascend Performance Materials name, brands, marks and logos (e.g., those identified with ®, ™, or SM) are owned by Ascend Performance Materials Operations, unless otherwise noted.

Vydyne® R530H BK0201

polyamide 66



Front Temperature	280 - 310	°C
Nozzle temperature	280 - 310	°C
Processing (Melt) Temperature	285 - 305	°C
Mold Temperature	65 - 95	°C



North America
+1 888 927 2363

Europe
+32 10 608 600

Asia
+86 21 2315 0888

Disclaimer

NOTICE: Although the information and recommendations set forth herein (hereinafter "information") are presented in good faith and believed to be correct as of the date hereof, Ascend Performance Materials Operations makes no representation or warranties as to the completeness of accuracy thereof.

Information is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purpose prior to use. In no event will Ascend Performance Materials Operations be responsible for damages of any nature whatsoever resulting in the use of or reliance upon information or the products to which information refers. Nothing contained herein is to be construed as a recommendation to use any product, equipment or formulation in conflict with any patent, and Ascend Performance Materials Operations makes no representation or warranty, express or implied, that use thereof will not infringe any patent. No representation or warranties, either express or implied, of merchantability fitness for a particular purpose or of any other nature are made hereunder with respect to information or product to which information refers.

CAUTION: Do not use Ascend Performance Materials Operations MED grades in medical applications involving implantation in the human body or contact with internal body fluids or tissues for extended periods of time.