

# Technical Data Sheet

PIR PP Regranulate natural

Product Code: 001510



**Description:** 001510 PP Regranulate natural was recovered from film rolls in Asia and is suitable for extrusion and film blowing applications.

Physical Properties	Value	Units	Standard
Density	0.905	g/cm <sup>3</sup>	ISO 1183
MFR (230°C, 2.16kg)	2.5	g/10 min.	ISO 1133
Tensile strength	26	MPa	ISO 527
Elongation at break	160	%	ISO 527
Izod notched impact strength	8.5	kJ/m <sup>2</sup>	ISO 180

## Disclaimer

This information contained herein is based on the data available to us and is believed to be correct. However, Sinox makes no warranty, expressed or implied, regarding the accuracy of this data or the results to be obtained from the use thereof. Each user of the products shall convince himself through all available sources (including finished product testing in its appropriate environment) of the suitability of the products supplied for its particular purpose.