

PC-ABS Mahlgut - Materialdaten

Produkt	PC-ABS Mahlgut
Verfügbarkeit	Kontinuierlich - jeden Monat

Materialwerte

Density	1,1
Melt Flow	~30
Ash Content	0
Flexural Modulus	1950
Izod Notched Impact	12
Tensile Strength	~40
Elongation at Break	~10

