

ADC&Partners BV
 New Yorkkaai 93 B 402
 B-2000 Antwerp
 VAT BE 0426.778.422
 Handy Nr +32 475 590323

TDS ADC PPC black granulate mfi 0,7

Date 24/05/1930

Description rPPCBL0,6

Properties Values

Polymer PP copo made from industrial waste

	Typical values	Units	Test Methods
Melt Flow Rate			
at 230 ° C and 2,16 kg	0,7	g / 10 min	ISO 1133
Density	0,911	g/cm3	ISO 1183
Humid content	< 0,10	%	
Izod impact strenghts notch	> 10	kJ/m2	ISO 180/A
Flex Modulus	1300	Mpa	ISO 178

Disclaimer

While the information here is given in good faith, seller makes no warranty, express or implied; including merchantability and noninfringer property, nor assumes any liability, direct or indirect, with respect to the performance, suitability or fitness for intended use or purpose of t application. Each customer must determine the suitability of seller materials for the costumer's particular use through appropriate testing ;

The TDS replaces all previous versions

These are test results, they may be differ from any other tests made later

ment of intellectual
these products in any