

# TABOREC BOPP 3-7 MIX R

## Description

**TABOREC BOPP 3-7 MIX R** is a PP regranulate from a stable source of BOPP foil.  
The grade is available in mixed colour and packed in big bags of 1000 kg.

## Properties

Properties		Test method	Unit	Typical values
Physical	Melt Flow Index (230°C/2,16 kg)	ISO 1133	g/10 min	3,0 - 7,0
	Ash content	ISO 3451-1	%	0 - 5,0
	Density	ISO 1183-1	g/cm <sup>3</sup>	0,94
	Volatiles	ČSN 64 0311	%	0 - 0,2
Mechanical	Tensile Strength	ISO 527	MPa	29
	Flexural Modulus	ISO 178	MPa	1 200
Impact	CHARPY Notched Impact Strength	ISO 179-1/1eA 23°C	kJ/m <sup>2</sup>	3,8
	CHARPY Unnotched Impact Strength	ISO 179-1/1eU 23°C	kJ/m <sup>2</sup>	NB
<b>Notes*</b> The above values (ranges) are typical for this material, not standardized.				