

Standridge Color

Wednesday May 6 2020

Plastics Innovation - Transforming Ideas Into Reality

ISO Certified Quality System

Technical Data Sheet



Code: 19SAM07152 BIESHEIM BLUE 072219

This is a Colorant compound dispersed into a Polypropylene resin and should process without any hesitancy at normal extrusion conditions.

Carrier Resin

Type:	PP	
Melt Flow:	25	g/10 min
Density:	.93	g/cm3

Concentrate / Compound

Pigment/Additive Loading:	20	%
Melt Flow:	20	g/10 min
Specific Gravity:	1.1	g/cm3
Heat Stability:	500	F
Pellets per Gram:	50	
CONEG Compliant:	YES	
FDA Approved:	NO	

Standridge Color Corporation
1196 East Hightower Trail
Social Circle, GA. 30025
770.464.3362

sales@standridgecolor.com
www.standridgecolor.com

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained there from. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variation in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the application disclosed. Full-scale testing and end product performance are the responsibility of the user. Standridge Color Corporation shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond Standridge Color Corporation's direct control. STANDRIDGE COLOR CORPORATION MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.