

ECOYADI-2 Sp. Z o.o.

Material				
PP GF40 8810 Black				
Properties	Average	Units	Standard	Conditions
Melt Flow Rate	22	g/10min	ISO 1133	230°C/2.16KG
Impact Strength	4	KJ/m²	ISO 180/1A	
Total Bromine content(Br)	ND	mg/kg	2011/65/EU	
Total chromlum content (Cr)	ND	mg/kg	2011/65/EU	
Cadmulum content(Cd)	ND	mg/kg	2011/65/EU	
Lead content(Pb)	ND	mg/kg	2011/65/EU	
Mercury content(Hg)	ND	mg/kg	2011/65/EU	
Color Data (L)	29			
Color Data (A)	-			
Color Data (B)	-			

