

DATA SHEET

and general product information

Characteristics:

Thermoplastic polyester/polyether-polyurethane with good mechanical properties, such as good wear resistance, excellent damping and recovery properties, good flexibility at cold temperatures.

Applications :

Injection moulding and also use in extrusion - for example : hoses, traffic restrictions like pylons, shoe soles, railway pads and much more.

Delivery form and packaging:

Granules, BigBags on disposable pallets, or Octabins upon request.

Colour :

Natural transparent to opaque - uncoloured

Characteristic	Unit	Range	Test Method/Standard
Hardness	Shore A	85. +/-5	DIN 53505-A
Density	g/cm ³	1,18 +/- 0.05	DIN EN ISO 1183-1
Ignition Residue	650°C/2h	<2%	DIN EN ISO 3451-1

DATA SHEET

and general product information

Characteristics:

Thermoplastic polyester/polyether-polyurethane with good mechanical properties, such as good wear resistance, excellent damping and recovery properties, good flexibility at cold temperatures.

Applications :

Injection moulding and also use in extrusion - for example : hoses, traffic restrictions like pylons, shoe soles, railway pads and much more.

Delivery form and packaging:

Granules, BigBags on disposable pallets, or Octabins upon request.

Colour :

Natural transparent to opaque - uncoloured

Characteristic	Unit	Range	Test Method/Standard
Hardness	Shore A	85. +/-5	DIN 53505-A
Density	g/cm ³	1,18 +/- 0.05	DIN EN ISO 1183-1
Ignition Residue	650°C/2h	<2%	DIN EN ISO 3451-1