

Technical Data sheet

Faroplast 01

VI NOVA d.o.o.
Arkova ulica 13
5280 Iridja
Slovenia


Product description

Faroplast 01 is 100 % recycled PVC/PVDC industrial waste material from pharmaceutical industry.


Rheological properties	Value	Unit	Test Standard
Melt flow index (175°C, 10kg)	0,09	g/10	ISO 1133
Mechanical properties	Value	Unit	Test Standard
Flexural modulus	2,2	GPa	ISO 178
Flexural strength	49,2	MPa	ISO 178
Flexural strain at flexural strength	4,3	%	ISO 178
Tensile modulus	2,2	GPa	ISO 527, 1BA
Tensile strength	34,1	MPa	ISO 527, 1BA
Strain at tensile strength	2,9	%	ISO 527, 1BA
Nominal strain at break	3,1	%	ISO 527, 1BA
Impact strength at 25 °C (Charpy)	16,3	kJ/m ²	ISO 179
Notched impact strength at 25 °C (Charpy)	3,8	kJ/m ²	ISO 179
Thermal properties	Value	Unit	Test Standard
Glass transition temperature	76,2	°C	ISO 11357-3
Melting temperature	114,0	°C	ISO 11357-3
Degradation temperature	271/311/447	°C	ISO 6964
Ash content	13,0	%	ISO 6964

* - all measurements were performed at the Faculty of Polymer Technology (www.ftpo.eu)

Dynamic mechanical analysis



σ - ϵ diagram – tensile test – left (ISO 527) in flexural test – right (ISO 178)



Recommendations for processing

Screw speed	low
Back pressure	moderate
Injection speed	low
Hold pressure	low to moderate
Mould temperature	40 °C – 50 °C
Melt temperature*	max. 165 °C
Moisture content	max. 0,1 %
Drying	4 hours at 70 °C

* - higher melt temperature causes degradation

DISCLAIMER OF LIABILITY

The data presented in this sheet reflect typical values obtained in the FTPO laboratories, but should not be considered as absolute or guaranteed values. The information, data and recommendations in this document have been obtained in good faith from reliable sources. VI NOVA d.o.o. is not responsible for problems that appear on the finished products, packaging or their components. We believe that the information provided in this document is correct and accurate, but any recommendations, statements or suggestions in this document are without any guarantee or warranty and do not establish any legal basis, duty or responsibility on the part of the author or his employer.

The user is responsible for the use, storage, handling and disposal of the material described above.