

Dynisco Polymer Test

MI MODEL: 4003 VYROB. CÍSLŮ: 5141 PRUM. TRYSKA.: 2.095mm
 ID PRÍSTROJ: 1 VERZE : DELKA TRYSKA.: 8.00mm
 PROGRA #: 3 ID PROGRAM: **HDPE-Regrind**
 METODA: B TEPLŮTA.: 190.0 PREDEHREV: 240 sec
 ZAVAZI: 5.00 kg PRÁPOREK: 3.175 mm HUSTOTA: 0.759 g/cc
 AUTO ODMITN: VYP
 DATUM: 03/ 4/19 ID PROBE : HUSTOTA/23C/ 0.951
 CAS : 15:57 OBSLUHA ID: VAVRIKOVA

RUN	FLAG	F.TIME	MFR	S.STRESS	S.RATE	VISC	TIME	TEMP	QC
#	#	sec	g/10min	Pa	1/sec	Pa-sec	sec	deg C	
1	1	302.25	0.340	45141	0.83	54586.8	1096.28	190.0	
1	2	304.33	0.338	45141	0.82	54962.6	1512.03	190.0	
1	3	305.03	0.337	45141	0.82	55088.8	1927.82	190.0	
Average			0.338		0.82	54879.4			
Standard Dev			0.002		0.00	261.2			
Coef of Variance			0.477		0.48	0.5			

BKP Plastics s.r.o.
 L. Podjavorinskej 2575/3B
 915 01 Nové Mesto nad Váhom
 IČO: 51 176 840
 IČ DPH: SK2120625067



J. F. ROST