



A~Star Plastics Pte Ltd

No. 1 Pioneer Place, Singapore 627866
Tel: +65-67088029 | Fax: +65-6250 1920
www.AstarPlastics.com

Company & GST Registration #: 201504765Z

Technical Data Sheet

Material Type: PMMA OFF GRADE RESIN

Grade: PMMA-MH00IJ-002

Colour: NATURAL

Application: General purpose extrusion and injection application

<u>Physical</u>	<u>Value</u>	<u>Unit</u>	<u>Test Method</u>
Density	1.18	g/cm ³	ASTM D792
Melt Flow Index at 230°C, 3.8 kgf	1 - 5	g/10min	ASTM D1238
Water Absorption, 23°C	0.3	%	ASTM D570
<u>Mechanical</u>	<u>Value</u>	<u>Unit</u>	<u>Test Method</u>
Tensile Strength at yield	74 ± 2	MPa	ASTM D638
Tensile Elongation at break	> 3	%	ASTM D638
Izod Impact, notched, 23°C	1.5 ± 0.5	kgf.cm/cm	ASTM D256
<u>Thermal</u>	<u>Value</u>	<u>Unit</u>	<u>Test Method</u>
Heat Deflection Temperature at 1.82 Mpa	95 - 100	°C	ASTM D648

Processing Condition

<u>Temperature</u>	<u>Value</u>	<u>Unit</u>
Melt Temperature	220 - 250	°C
Rear Barrel Temperature	220 - 240	°C
Middle Barrel Temperature	230 - 250	°C
Front Barrel Temperature	230 - 250	°C
Nozzle Temperature	220 - 240	°C
Mould Temperature	60 - 80	°C
Drying Temperature	75 - 85	°C
Drying Time	4	hour

The information should only be used as a reference guide.

A~Star Plastics makes no warranties of the product for any particular use or purpose.

Enquiry: exports@astarplastics.com