

# SALES SPECIFICATION

<b>Name</b>	<b>PP light gray regrind</b>
<b>Form</b>	<b>Regrind in the form of pieces of plastic.</b>
<b>Composition</b>	<b>Mainly PP (98-100%). The sum of the share of other materials (ABS, PS) up to 2% by weight the entire faction. The materials contain fillers of approx. 30% calcium carbonate/talc and residual amounts of glass fibre.</b>
<b>Impurities</b>	<b>Permissible up to 1% of the total impurities in the form of chipboard.</b>
<b>Color</b>	<b>White with an admixture of grey and black flakes.</b>
<b>Size</b>	<b>0-31,5 mm</b>
<b>Bulk Density</b>	<b>300-400 kg/m<sup>3</sup></b>
<b>MFI</b>	<b>6-10 g/10 min (2,16 kg, 230°C)</b>
<b>Humidity</b>	<b>max. 3,0 % H<sub>2</sub>O</b>

**Packing Way:**  
**Big-bag bags on pallets 95x95x190 cm.**

