

## HDPE Regrinded (Injection Grade)



Black

Specifications	Method	Limits
<b>MFI</b> (g/10') 190°C 5kg	ISO 1133-1	[1,2-1,6]
<b>Density</b> (Kg/m <sup>3</sup> )	NP EN 15344 Anex B	[0,90; 0,96]
<b>Grain diameter</b> (mm) Fração >75%	ASTM D1921 Method A	[5 - 12]
<b>Humidity</b> %		≤ 0,20
<b>% not plastic</b>	Gravimetria	≤ 1%
<b>% non-target typology</b>	FTIR	≤ 2%
<b>Dangerousness</b>	-	Not dangerous according to Regulations CLP, REACH and POPs

### Intended use

injection process

### Exclusions

Food grade applications

### Packaging

Big-bag on pallet