

Fromto Recycling NV

Europark 1075, 3530 Houthalen-Helchteren

BTW-nr.: BE0439.289.343

info@ecoo.eu | +32 | 1 45 41 46 | www.ecoo.eu

Product Data Sheet

Product Code: F2-FP-12-BL-NN-50-EX

(short code 7815BL)

Polymer composition: (LLD)PE > 35% / PP > 40% / PET < 15%

Product Description : A mixture of colored post-consumer low density polyethylene and other polyolefins supplied in pellet form, without additives. It originates from pre-sorted municipal (household) waste

containing mostly PE and PP film. **Application:** used for extrusion.

It is not intended for use in food contact, water contact, pharmaceutical

and medical applications.



General Characteristics

Form : Granules Size : 4 +/- 0,5mm Filtration : 1200 μm Color : Black

Packaging: Preferably delivered in 25 ton bulk. Big bags are possible.

Due to the nature of recyclates, some variation in product properties can be observed between batches. For that reason average values are indicated.

Physical & Mechanical Characteristics

Density: 990 kg/m³ (ISO 1183)

Melt Mass-Flow Rate (MFR): 5.02 g/10 min (ISO 1133 - 230°C/2.16 kg)

Residual moisture (30 min/100°C) : < 0.30 % Tensile Modulus : 928 MPa (ISO 527-1)

Tensile Strength (at break) : 15.8 MPa (ISO 527-2) Tensile Elongation (at break) : 14 % (ISO 527-2)

Flexural Modulus: 867 MPa (ISO 178)

Impact Strength (Charpy Test) at 23°C: 13.3 kJ/m²) (ISO 179) Impact Strength (Charpy Test) at -15°C: 2.8 kJ/m² (ISO 179)

Other Characteristics

Melting Point (LLD)PE : 106 - 128 °C (ISO 11357-1) Melting Point PP : 160 - 164 °C (ISO 11357-1) Melting Point PET : 249 - 251 °C (ISO 11357-1)

Ash Content: 2,7 % (ISO 3451)

Version 09-05-2025

Disclaimer

The liability of FROMTO is strictly limited to the features and provisions laid out in this product data sheet. No claims, representations or warranties, whether express or implied, are made by FROMTO as to the processability of the products. Once a buyer uses, processes (whether or not in combination with other products) or handles a product of FROMTO, FROMTO does not accept any kind of liability whatsoever as to the safety, reliability, processability, durability and performance of the products subject to usage, processing or handling.

