



Technical Datasheet

Code

PSH-99RE10

PSH REGRANULAT Coloured

	Standard	Unit	Specification	Value
MFR - melt flow rate	ISO 1133	g/10 min	200 °C - 5 kg	8,20
Flexural Modulus	ISO 178	MPa		1864
Density	ISO 2781	g/cm ³		1,049
IZOD Impact strength at 25 °C	ISO 179	kJ/m ²		12,78
Notched impact strength at 25 °C (Charpy)	ISO 179	kJ/m ²		2,76

The data above is provided in good faith and represents typical properties based on our current knowledge and experience.

Product properties may be changed without notice. These properties are provided as a guide and should not be construed as binding specification limits or minimum values.

This document does not create any liability, warranty or guarantee of product performance.

It is the customer's responsibility to determine the suitability of KRM products for the intended application.

KRM Kunststoff – Recycling – Maschinen GmbH

UID-Nr.: ATU57651838 | Landesgericht Klagenfurt | FN 244405 w

A-9125 Kühnsdorf | Mitte 68

www.krm-recycling.com



RecyClass