

Technical Datasheet

Code	PPC-11RE20
	PPC REGRANULATE Light Gray

	Standard	Unit	Specification	Value
MFR - melt flow rate	ISO 1133	g/10 min	230 °C - 2,16 kg	**20,40**
Flexural Modulus	ISO 178	MPa		**746**
Density	ISO 2781	g/cm³		**0,975**
IZOD Impact strength at 25 °C	ISO 179	kJ/m²		**don't break**
IZOD Notched impact strength at 25 °C	ISO 179	kJ/m²		**6,79**
Ash Content	ISO3451-1	%		**9,2**

The data above is provided in good faith and represents typical properties based on our current knowledge and experience.
Product properties may be changed without notice. These propereties are provided as a guide and should not be construed as binding specification limits or minimum values.
This document does not create any liability, warrenty or guarentee of product performance.
It is the customer's responsibility to determine the suitability of KRM products for the intended application. The measured values may deviate by plus or minus 5 percent.

KRM Kunststoff – Recycling – Maschinen GmbH
UID-Nr.: ATU57651838 | Landesgericht Klagenfurt | FN 244405 w
A-9125 Kühnsdorf | Mitte 68
www.krm-recycling.com