


HDPE, Industrial Packaging

Large Blow Molding



Properties	Physical		Mechanical			Tensile Impact Strength		Others		Specific characteristics and typical customer applications
	Density 23°C ISO 1183	MFR 190°C/ 21.5 kg ISO 1133	Tensile modulus	Tensile Stress at Yield ISO 527	Tensile Elongation at Yield	Notched -30°C	ESCR (FNCT): 3.5 MPa, 80°C, 2% aqueous)	ESCR (Basell bottle test)	Delivery Form	
TEST METHOD	g/cm ³	g/10 min	MPa	MPa	%	kJ/m ²	h	Basell		
PRODUCT GRADES – HDPE										
Lupolen 4261 AG Q469	0.945	6	850	24	10	170	60	4000	pellet	Outstanding ESCR; high impact resistance; good chemical resistance; Jerry Cans (also coex); packaging of dangerous goods
Lupolen 4261 AG UV 60005	0.945	6	850	24	10	170	60	4000	pellet	UV stabilized; outstanding ESCR; high impact resistance; good chemical resistance; Jerry Cans; IBC; HOT; packaging of dangerous goods
Lupolen 4261 A Q149	0.945	6	850	24	10	170	60	4000	powder	Outstanding ESCR; high impact resistance; good chemical resistance; additive free; Jerry Cans, Drums (high purity applications, coex)
Lupolen 4261 AG Q474	0.945	6.5	850	24	10	170	60	4000	pellet	Outstanding ESCR; high impact and good chemical resistance; injection molded IBC outlet valves and accessories; packaging of dangerous goods
Lupolen 5261 ZS	0.951	2	1000	26	9	250	20	700	powder	High ESCR; high impact resistance; high rigidity; high chemical resistance; Jerry Cans; Drums; packaging of dangerous goods
Lupolen 5121 A	0.951	5	1050	25	7	150	16	-	pellet	High rigidity; high ESCR; good flowability; very good impact resistance; Jerry Cans; packaging of dangerous goods
Hostalen ACP 5331 A	0.952	6.5	1050	26	10	150	50	-	pellet	Excellent combination of stiffness and ESCR; very good impact resistance; Jerry Cans and Drums; packaging of dangerous goods
Lupolen 5261 Z	0.954	2	1200	27	9	250	11	130	powder	Good ESCR; high impact resistance; high rigidity; high chemical resistance; Jerry Cans; Drums; packaging of dangerous goods
Lupolen 5261 Z HI	0.954	2	1200	28	8	280	14	130	powder	Outstanding impact resistance; good ESCR; high rigidity; L-Ring Drums; packaging of dangerous goods
Hostalen ACP 5531 B	0.954	9.5	1250	27	10	90	40	400	pellet	Excellent combination of stiffness and ESCR; high rigidity; good impact resistance; Jerry Cans; packaging of dangerous goods
Purell ACP 5531 B	0.954	9.5	1250	27	10	90	40	400	pellet	Excellent combination of stiffness and ESCR; high rigidity, dedicated grade for healthcare applications; Jerry Cans
Hisstiff 5431 Z	0.954	2.6	1200	27	8	290	14	-	pellet	Outstanding impact resistance; good ESCR; high rigidity; L-Ring Drums; packaging of dangerous goods
Hostalen GM 9350 C black	0.995	3	1200	28	7	45	90	-	pellet	Conductive grade (carbon black), outstanding ESCR, good chemical resistance, limited impact resistance; Jerry Can, Drum (coex), IBC (coex)

*HOT = Heating Oil Tank, ESCR = Environmental Stress Crack Resistance, FNCT = Full Notch Creep Test, IBC = Intermediate Bulk Container.

You can find out more about us by visiting our website at: www.lyb.com

Before using a product sold by a company of the LyondellBasell family of companies, users should make their own independent determination that the product is suitable for the intended use and can be used safely and legally. SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED (INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY WARRANTY) OTHER THAN AS SEPARATELY AGREED TO BY THE PARTIES IN A CONTRACT. This product(s) may not be used in: (i) any U.S. FDA Class I, Health Canada Class I, and/or European Union Class I Medical Devices, without prior notification to Seller for each specific product and application; (ii) the manufacture of any of the following, without prior written approval by Seller: (1) U.S. FDA Class II, Health Canada Class II or Class III, and/or European Union Class II Medical Devices; (2) film, overwrap and/or product packaging that is considered a part or component of one of the aforementioned Medical Devices; (3) packaging in direct contact with a pharmaceutical active ingredient and/or dosage form that is intended for inhalation, injection, intravenous, nasal, ophthalmic (eye), digestive, or topical (skin) administration; (4) tobacco related products and applications; (5) electronic cigarettes and similar devices; and (6) pressure pipe or fittings that are considered a part or component of a nuclear reactor; (iii) Additionally, the product(s) may not be used in: (1) U.S. FDA Class III, Health Canada Class IV, and/or European Class III Medical Devices; (2) applications involving permanent implantation into the body; (3) life-sustaining medical applications; and (4) lead, asbestos or MTBE related applications. All references to U.S. FDA, Health Canada, and European Union regulations include another country's equivalent regulatory classification. Users should review the applicable Material Safety Data Sheet before handling the product.

Lupolen, Hostalen, Hisstiff and Purell are trademarks owned or used by LyondellBasell group companies. Lupolen, Hostalen, and Purell are registered in the U.S. Patent and Trademark Office.