

Ex-Grilamid L25W40

<b>Lot: PHPCY</b>	<b>PA12</b>	<b>Method</b>	<b>Unit</b>	<b>verified values</b>
MFR	2.16Kg./ 235°C	ISO 1133	g/10min	<b>3,50</b>
Relative Humidity		M.I.	%	<b>0,10</b>
Flexural modulus	1 mm/min	ISO 527/2	Mpa	<b>460</b>
Tensile Test	50 mm/min	ISO 527/2	Mpa	<b>26</b>
Melting point	10°C/min	M.I.	°C	<b>174</b>