

Ex-Grilamid L 20 G				
Lot: PHTOC	PA12	Method	Unit	verified values
MFR	2.16Kg./ 235°C	ISO 1133	g/10min	6,30
MFR	5.00Kg./ 275°C	ISO 1133	g/10min	50
Tensile Strength		ISO 527	Mpa	37
Tensile Modulus		ISO 527	Mpa	1150
Elongation at Break		ISO 527	%	> 30
Melting point	10°C/min	M.I.	°C	173