

VALOX™ 357X resin

Monday, June 5, 2017

General Information

Product Description

VALOX 357X is an impact modified, flame retarded PBT+PC blend. Applications like bobbins, switches and enclosures.

General

Material Status	• Commercial: Active
Availability	• Europe
Additive	• Flame Retardant • Impact Modifier
Features	• Flame Retardant • Impact Modified
Uses	• Bobbins • Housings • Switches
RoHS Compliance	• RoHS Compliant
Processing Method	• Injection Molding

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.34	g/cm ³	ASTM D792
Density	1.34	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)			ASTM D1238
250°C/5.0 kg	9.6	g/10 min	
265°C/5.0 kg	13	g/10 min	
266°C/5.0 kg	13	g/10 min	
Melt Volume-Flow Rate (MVR)			ISO 1133
250°C/5.0 kg	8.00	cm ³ /10min	
265°C/5.0 kg	10.0	cm ³ /10min	
Molding Shrinkage - Flow			Internal Method
-- ²	1.1 to 1.8	%	
3.20 mm	1.0 to 1.4	%	
Molding Shrinkage - Across Flow ²	0.90 to 1.8	%	Internal Method
Water Absorption (Saturation, 23°C)	0.50	%	ISO 62
Water Absorption (Equilibrium, 23°C, 50% RH)	0.15	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ³	2000	MPa	ASTM D638
Tensile Modulus	2200	MPa	ISO 527-2/1
Tensile Strength ⁴ (Yield)	50.0	MPa	ASTM D638
Tensile Stress (Yield)	50.0	MPa	ISO 527-2/50
Tensile Strength ⁴ (Break)	40.0	MPa	ASTM D638
Tensile Stress (Break)	40.0	MPa	ISO 527-2/50
Tensile Elongation ⁴ (Yield)	5.0	%	ASTM D638
Tensile Strain (Yield)	5.0	%	ISO 527-2/50

Disclaimer : THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with ™ are trademarks of SABIC or its subsidiaries or affiliates.

© 2017 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.

VALOX™ 357X resin

SABIC Innovative Plastics Europe - Polycarbonate + PBT

Mechanical	Nominal Value	Unit	Test Method
Tensile Elongation ⁴ (Break)	30	%	ASTM D638
Tensile Strain (Break)	30	%	ISO 527-2/50
Flexural Modulus ⁵ (50.0 mm Span)	2100	MPa	ASTM D790
Flexural Modulus ⁶	2000	MPa	ISO 178
Flexural Stress ^{6, 7}	80.0	MPa	ISO 178
Flexural Strength ⁵ (Yield, 50.0 mm Span)	78.0	MPa	ASTM D790
Taber Abrasion Resistance 1000 Cycles, 1000 g, CS-17 Wheel	33.0	mg	Internal Method
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			
-30°C ⁸	20	kJ/m ²	ISO 179/1eA
-30°C	20	kJ/m ²	ISO 179/2C
23°C ⁸	45	kJ/m ²	ISO 179/1eA
23°C	40	kJ/m ²	ISO 179/2C
Charpy Unnotched Impact Strength			
-30°C ⁸	No Break		ISO 179/1eU
-30°C	No Break		ISO 179/2U
23°C ⁸	No Break		ISO 179/1eU
23°C	No Break		ISO 179/2U
Notched Izod Impact			ASTM D256
-30°C	150	J/m	
0°C	190	J/m	
23°C	500	J/m	
Notched Izod Impact Strength ⁹			ISO 180/1A
-30°C	10	kJ/m ²	
0°C	20	kJ/m ²	
23°C	40	kJ/m ²	
Unnotched Izod Impact			ASTM D4812
-30°C	No Break		
23°C	No Break		
Unnotched Izod Impact Strength ⁹			ISO 180/1U
-30°C	No Break		
23°C	No Break		
Instrumented Dart Impact (23°C, Total Energy)	35.0	J	ASTM D3763
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	115		ISO 2039-2
Ball Indentation Hardness (H 358/30)	115	MPa	ISO 2039-1
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 0.45 MPa, Unannealed, 3.20 mm	130	°C	ASTM D648

Disclaimer : THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with ™ are trademarks of SABIC or its subsidiaries or affiliates.

© 2017 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.

VALOX™ 357X resin

SABIC Innovative Plastics Europe - Polycarbonate + PBT

Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed, 100 mm Span ¹⁰	135	°C	ISO 75-2/Be
0.45 MPa, Unannealed, 64.0 mm Span ¹¹	130	°C	ISO 75-2/Bf
Deflection Temperature Under Load			ASTM D648
1.8 MPa, Unannealed, 3.20 mm	85.0	°C	
Heat Deflection Temperature			
1.8 MPa, Unannealed, 100 mm Span ¹⁰	85.0	°C	ISO 75-2/Ae
1.8 MPa, Unannealed, 64.0 mm Span ¹¹	85.0	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	180	°C	ASTM D1525 ¹²
--	145	°C	ASTM D1525 ¹³
Vicat Softening Temperature			
--	180	°C	ISO 306/A50
--	145	°C	ISO 306/B50
--	150	°C	ISO 306/B120
Ball Pressure Test (125°C)	Pass		IEC 60695-10-2
CLTE - Flow (-40 to 40°C)	9.2E-5	cm/cm/°C	ASTM E831
CLTE - Flow (23 to 80°C)	1.0E-4	cm/cm/°C	ISO 11359-2
CLTE - Transverse (-40 to 40°C)	8.4E-5	cm/cm/°C	ASTM E831
CLTE - Transverse (23 to 80°C)	1.0E-4	cm/cm/°C	ISO 11359-2
Thermal Conductivity	0.17	W/m/K	ISO 8302
RTI Elec	120	°C	UL 746
RTI Imp	120	°C	UL 746
RTI Str	140	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms·cm	ASTM D257
Volume Resistivity	> 1.0E+15	ohms·cm	IEC 60093
Dielectric Strength			ASTM D149
1.60 mm, in Oil	25	kV/mm	
3.20 mm, in Oil	17	kV/mm	
Electric Strength			IEC 60243-1
0.800 mm, in Oil	34	kV/mm	
1.60 mm, in Oil	25	kV/mm	
3.20 mm, in Oil	17	kV/mm	
Dielectric Constant (1 MHz)	3.00		ASTM D150
Relative Permittivity			IEC 60250
50 Hz	3.00		
60 Hz	3.00		
1 MHz	3.00		
Dissipation Factor (1 MHz)	0.013		ASTM D150

Disclaimer : THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with ™ are trademarks of SABIC or its subsidiaries or affiliates.

© 2017 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.

VALOX™ 357X resin

SABIC Innovative Plastics Europe - Polycarbonate + PBT

Electrical	Nominal Value	Unit	Test Method
Dissipation Factor			IEC 60250
50 Hz	2.0E-3		
60 Hz	2.0E-3		
1 MHz	1.3E-3		
Arc Resistance ¹⁴	PLC 6		ASTM D495
Comparative Tracking Index (CTI)	PLC 3		UL 746
Comparative Tracking Index			IEC 60112
--	225	V	
Solution B	100	V	
High Amp Arc Ignition (HAI)	PLC 0		UL 746
High Voltage Arc Tracking Rate (HVTR)	PLC 3		UL 746
Hot-wire Ignition (HWI)	PLC 3		UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.75 mm	V-0		
2.5 mm	5VA		
Glow Wire Flammability Index (1.0 mm)	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature			IEC 60695-2-13
1.0 mm	825	°C	
2.0 mm	725	°C	
3.0 mm	700	°C	
Oxygen Index	30	%	ISO 4589-2
Fill Analysis	Nominal Value	Unit	Test Method
Melt Viscosity (260°C, 1500 sec ⁻¹)	310	Pa·s	ISO 11443

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	110 to 120	°C
Drying Time	2.0 to 4.0	hr
Suggested Max Moisture	0.020	%
Hopper Temperature	40 to 60	°C
Rear Temperature	230 to 245	°C
Middle Temperature	240 to 255	°C
Front Temperature	245 to 265	°C
Nozzle Temperature	240 to 260	°C
Processing (Melt) Temp	250 to 270	°C
Mold Temperature	40 to 100	°C

Disclaimer : THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with ™ are trademarks of SABIC or its subsidiaries or affiliates.

© 2017 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.

VALOX™ 357X resin

SABIC Innovative Plastics Europe - Polycarbonate + PBT

Notes

¹ Typical properties: these are not to be construed as specifications.
² Tensile Bar
³ 50 mm/min
⁴ Type I, 50 mm/min
⁵ 1.3 mm/min
⁶ 2.0 mm/min
⁷ Yield
⁸ 80*10*4 sp=62mm
⁹ 80*10*4
¹⁰ 120*10*4 mm
¹¹ 80*10*4 mm
¹² Rate A (50°C/h), Loading 2 (50 N)
¹³ Rate B (120°C/h), Loading 2 (50 N)
¹⁴ Tungsten Electrode

Disclaimer : THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES (“SELLER”) ARE SOLD SUBJECT TO SELLER’S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER’S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER’S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller’s materials, products, services or recommendations for the user’s particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller’s Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.