

High Density Polyethylene SGF4950

Description:

SGF4950 is a high-density polyethylene copolymer, developed for the blow-molding segment. It shows well balanced properties between impact and stiffness, combined with high environmental stress cracking resistance and processability. The minimum biobased carbon content of this grade is 96%, determined according to ASTM D6866.

Aplicações:

Tissue and hygiene packaging, Blow molding small volumes, Cosmetic packaging

Processos:

Compression Molding, Extrusion Blow Molding

Control Properties:

Característica	Método	Unidades	Valores
Melt Flow Rate (190°C/2.16kg)	D 1238	g/10 min	0.34
Density	D 792	g/cm ³	0.956

Typical Properties:

Plaque Properties

Característica	Método	Unidades	Valores
Melt Flow Rate (190°C/21,6kg)	ASTM D 1238	g/ 10 min	28
Tensile Strength at Yield (a)	ASTM D 638	MPa	30
Tensile Strength at Break (a)	ASTM D 638	MPa	30
Flexural Modulus - 1% Secant (b)	ASTM D 790	MPa	1250
Tensile Impact Strength ISO at 23 °C	ISO 8256	kJ/m ²	110
Environmental Stress Cracking Resistance - notch 0,3 mm; 50°C; 10% Igepal CO630 (a)	ASTM D 1693	h/F50	30
Deflection Temperature under Load at 0.455 MPa (b)	ASTM D 648	°C	70
Vicat Softening Temperature at 10 N (b)	ASTM D 1525	°C	127

Typical properties correspond to average values obtained in our laboratories. Test specimens prepared from compression molded sheet made according to ASTM D 4703. Thickness of test piece: a) 2 mm; b) 3 mm.

Final Remarks

1. It is the sole responsibility of the Client/Purchaser of this Product to verify the suitability of this Product and its use for the intended use and to ensure compliance with legal and regulatory requirements applicable to the final product.
2. The technical guidance eventually rendered to the Client/Purchaser of the Product by Braskem about the Product does not characterize a performance guarantee for the intended application, nor does it exempt the Client/Purchaser from the responsibilities described in item 1 above.
3. Any application information about the Product does not mean that Braskem knows or has validated the productive process of the Client/Purchaser or the adequacy of the Product for the intended application. All warranties of merchantability or fitness for a particular purpose, express or implied, are expressly excluded.
4. The information provided herein is of the date hereof and Braskem may update, revise or amend the information contained herein at any time and without previous notice. The Client/Purchaser shall consult www.braskem.com to verify any updates to this information.
5. For regulatory information associated with the Product and its source, please consult the Regulatory Information Sheet (RIS). For other requests, please contact Braskem's Technical Services area.
6. The information contained herein is provided based on the best of Braskem's knowledge, indicating typical values of the properties of the Product, and such values shall not be considered absolute or as a guarantee.